

Wire Rope





8x19 Class


8 x 19 Class IWRC Rotation Resistant Improved Plow Steel Galvanized and Extra Improved Plow Steel Uncoated











Nominal Diameter (minimum)	Approx. Weight	Nominal Breaking Strength	
		Bright	Galvanized
	IWRC	IWRC	IWRC
inches	lb/ft	lb/ft	lb/ft
3/8	0.26	13,260	13,260
1/2	0.47	23,200	23,200
9/16	0.60	29,400	29,400
5/8	0.73	36,200	36,200
3/4	1.06	51,800	51,800
7/8	1.44	70,000	70,000
1	1.88	91.000	91,000

- · All Premium and standard quality imported ropes are RR-W-410, recent revision, as applicable.
- *Breaking strength listed for comparative purposes. Operating loads may vary, but NEVER exceed the recommended design factor of 20% of the Breaking strength.