



- Quenched and Tempered Alloy Steel.
- At least 25% greater WLL than traditional G80 products.
- Manufactured in accordance with EN 1677- 1 and ASME B30.26.
- Proof Load tested at 2.5 times the WLL with certification for each batch manufactured.
- Design Factor 4:1.
- Fatigue rated to 20,000 cycles at 1.5 times the WLL.
- Tempering temperature minimum 400°C
- Magnaflux crack detection is performed 100% on each batch.

G-100 Clevis Shackle

Item No.	For Grade 100 Chain	WLL tonnes*	Dimensions (mm)							N.W. kg
	mm		A	C	G	K	L	M	W	
X-066-07	7,8	2.5	9	79	34	59	35	16	33	0.4
X-066-10	10	4.0	11	93	40	78	48	20	37	0.8
X-066-13	13	6.7	14	118	44	98	64	22	49	1.4
X-066-16	16	10.0	18	141	54	112	69	28	60	2.5

★ Design factor 4:1 proof tested and certified